

**PRODUCT: HEMP PROPYLENE 25%**

**Description:**

H25CPP1 is a 25% hemp filled polypropylene. This product is generally used in injection molding, but may be used for other forming methods as developed by individual users. HEMP PROPYLENE is designed to be a drop-in replacement for conventional fossil fuel based polymers.

Natural color is medium brown; pelletized. Refer to molding recommendations below; limiting back pressure and injection speed as much as process will allow is optimal for working with this material.

<b>Property:</b>	<b>Typical Value:</b>	<b>Units:</b>	<b>Test Method:</b>
Specific Gravity	0.98	g/cc	ASTM D 792
Tensile Strength @ Break	2,000	psi	ASTM D 638
Tensile Elongation @ Break	15.3	%	ASTM D 638
Flexural Modulus (2% secant)	153,800	psi	ASTM D 790
Melt Flow Index, 230C/2.16Kg	22.4	g/10 min	ASTM D 1238
Izod Impact	1.383	ft. lbs/in	ASTM D 256
Gardner Impact	40	ft*lbs	ASTM D 5420

**General Recommendations:**

<b>Temperatures (F)</b>		<b>Pressures</b>		<b>Other</b>
Back	270 – 330	Injection	Moderate	Injection Rate: Moderate
Middle	300 – 340	Hold	Moderate – High	Screw Speed: Moderate-Fast
Front	300 – 340	Back	Moderate	
Nozzle	310 – 370			
Mold	80 - 100			<b>Pre-drying</b> is recommended before molding to avoid potential for splay

Data are obtained from tests performed under carefully controlled conditions from representative samples of the compound described herein. Properties may be materially affected by molding techniques applied and by the size and shape of the item molded. No assurance can be implied that all molded articles will have the same properties as those listed.

This information serves only as a guideline for processors, users and manufacturers. Due to the complex nature of design and processing, observation on a “trial and error” basis may be required to achieve desired results.

No information supplied by The Hemp Plastic Company (THPC) constitutes a warranty regarding product performance or use. Any information regarding performance or use is only offered as an approach for investigation for use, based upon THPC or other customer experience. THPC makes no warranties, expressed or implied, concerning the suitability or fitness of any of its products for any particular purpose. It is the responsibility of the customer to determine that the product is safe, lawful and technically suitable for the intended use.